



# CHR<sup>®</sup>

*A Saint-Gobain Brand*

Saint-Gobain

Performance Plastics

Pressure-Sensitive

Adhesive Tapes

  
SAINT-GOBAIN  
PERFORMANCE PLASTICS

# CHR<sup>®</sup>

## Pressure-Sensitive Adhesive Tapes

### ADHESIVE SYSTEMS

#### Acrylic (A)

Acrylic adhesives perform in continuous operating temperatures from -40°F to +375°F (-40°C to +188°C). Benefits include exceptional solvent resistance, excellent adhesion to metal, superior weathering and aging characteristics. Acrylics have an excellent shelf life, and when exposed to elevated temperatures, their ability to wet-out improves thus increasing both adhesion and tack properties.

#### Natural Rubber (R)

Natural rubber adhesives impart high tack and shear characteristics. These adhesives perform in continuous operating temperatures from -20°F to +325°F (-29°C to +164°C). Natural rubber adhesives can be specially blended to manufacture a broad range of adhesion performance from a low adhesion of 3.0 oz./in. to high adhesion of 60 oz. in.

#### Silicone (S)

Perfect for extreme temperature applications, silicone adhesives perform in continuous operating temperatures from -100°F to 500°F (-73°C to 260°C). Silicone-based adhesive systems exhibit good chemical resistance, retain electrical properties, and remove cleanly with little or no residue.

#### Thermosetting Organic Rubber (TR)

Thermoset adhesives set up or harden on first exposure to heat, and remain set regardless of subsequent temperature cycles. A blend of organic rubbers compounded with fillers, tackifiers, or curing agents, these adhesives have three primary benefits:

- Increased adhesion strength
- Improved solvent resistance
- Improved thermal capability

Thermoset Cycle:

#### Rubber PSA/Acrylic

3 hours @ 248°F (120°C)

2 hours @ 275°F (135°C)

1 hour @ 302°F (150°C)

### BACKING SUBSTRATES

#### Film-FEP

FEP film is used for applications requiring optical clarity, quick release, and abrasion resistance. FEP film applications include high temperature coil and capacitor wrapping, composite bonding, masking, and conveyor release linings.

#### Film-Polyester

Polyester films have excellent dimensional stability, high tensile, tear, and impact strengths, and ultimate elongation up to 120% of its original dimensions. These films exhibit low water absorption and good resistance to oils, greases, strong acids, and organic solvents. They also retain electrical properties, dielectric strength and dielectric constant in continuous operating temperatures from -100°F to 350°F (-73°C to 177°C). Applications include transformer and capacitor wrapping, printed circuit board fabrication, splicing tapes, composite bonding protection, and low-cost masking.

#### Film-Polyimide

Polyimide films are employed because of their extreme heat resistance. Service temperatures range from -100°F to +500°F (-73°C to +260°C). These flame retardant films exhibit high tensile strength and conformability, good solvent resistance, excellent dielectric strength and good abrasion resistance. Polyimide tape applications include electrical insulation, capacitor, transformer, and coil wrapping, electronic assembly, and wave solder protection.

#### Film-PTFE

PTFE films provide a conformable release surface and exhibit a remarkably low coefficient of friction and non-stick properties. PTFE films have high temperature resistance and are virtually unaffected by all chemicals. At elevated temperatures, PTFE film still retains excellent tensile strength. Service temperatures range from -100°F to +500°F (-73°F to +260°C).

Film applications include high temperature coil and capacitor wrapping, composite bonding, masking, and conveyor release linings.

#### Film-Rulon<sup>®</sup>

Rulon films offer superior abrasion resistance when compared to conventional PTFE films. Service temperatures range from -100°F to 500°F (-73°C to +260°C). In rotating bearing tests, it provided a 500-fold increase in wear resistance over standard PTFE. Applications include bearing liners, chute and guide rail coverings.

#### Film-UHMW

UHMW polyolefin film tape provides anti-sticking and abrasion resistance properties for application temperatures ranging from -100°F to 225°F (-73°C to +107°C). Applications include bearings, chute and guide rail coverings.

#### Glass-Cloth

Glass cloth offers excellent abrasion resistance and mechanical properties, as well as high tensile strength and extreme temperature resistance. Service temperatures range from -100°F to +500°F (-73°C to 260°C). Highly conformable and flexible, glass cloth has the unique ability to absorb insulating varnishes, which makes them an excellent choice in the electrical market. Applications include electrical insulation, coil and motor wrappings, and general industrial applications.

#### Glass-PTFE

PTFE glass provide dimensional stability, high tensile strength and edge tear, operates over a temperature range from -100°F to +500°F (-73°C to +260°C), and offers better abrasion resistance than uncoated glass cloth. The PTFE surface offers quick release and chemical resistance characteristics. Anti-static PTFE glass yields improved thermal conductivity and static dissipation. Available with silicone or acrylic adhesives, PTFE glass applications include heat sealing and low friction release surface liners for conveyors.

### **Glass-Silicone**

Silicone glass provides temperature resistance from -85°F to +500°F (-62°C to +260°C) and exceptional tensile strength and abrasion resistance. Applications include thermal spray, grit blasting, electrical and thermal insulation gaskets, heat sealing, and diaphragms.

### **Glass-Foil**

For applications requiring higher tear strengths, fiberglass laminated with aluminum is available. Service temperatures range from -100°F to 500°F (-73°C to +260°C).

### **Foils**

Aluminum and copper foil tapes offer high conformability, conductivity, and reflectivity at elevated temperatures. Aluminum is available with a fiberglass laminate for applications requiring higher tear strengths. Service temperatures range from -100°F to +500°F (-73°C to +260°C). Applications include thermal spray, aircraft repainting, EMI/RFI shielding, and electroplating.

### **Paper**

Paper tapes are designed to provide high temperature and excellent solvent resistance for wave soldering, printed circuit board masking, and hot air leveling applications. Service temperatures range from -100°F to 500°F (-73°C to +260°C).

### **Silicone Rubber (Strip-N-Stick®)**

*Strip-N-Stick* tape provides all the benefits of silicone rubber in an easy-to-apply, pressure-sensitive adhesive tape. Available in closed-cell sponge, low-density foam, or solid silicone, these products offer superior service life, excellent conformability and flexibility, low-compression set, and high adhesion to a variety of materials. Service temperatures range from -100°F to +500°F (-73°C to +260°C). Available with silicone or acrylic adhesives, Strip N Stick tape is excellent for high and low temperature gasket applications cushioning, thermal insulation, electrical isolation, and vibration dampening.

## **RELEASE LINERS**

### **Fluorosilicone**

This release liner incorporates advanced release technology for use with silicone adhesives. As a die-cuttable liner, it has exceptional release properties, making it an ideal choice when die-cutting small or complex parts.

### **Polyethylene**

These very thin release liners not only conform well to tape, but slit and release easily, making them a sensible choice for die-cutting. Available with acrylic or rubber adhesive systems, a smooth blue release liner is standard on most acrylic-adhesive pressure sensitive products.

### **PVC**

The most general purpose release liner, PVC conforms well to tape and protects the adhesive coating during handling. Although these liners have good release properties and slit well, they are generally not used for die-cutting. Only available with silicone adhesive tapes, a yellow-dimpled liner is standard.

### **Paper**

The ideal choice to die- and kiss-cutting, paper liners have the advantage of low cost and excellent release characteristics. Available with silicone, rubber and acrylic adhesive systems, these beige release liners are specially treated to ensure excellent release properties.

## **CUSTOM TAPES**

As a materials innovator, Saint-Gobain specializes in manufacturing unique products to satisfy customer needs. While this catalog details many of our standard pressure sensitive adhesive tapes, Saint-Gobain also offers custom tapes to meet application or customer specific requirements.

Part Number	Color	Adhesive System	Backing Thickness		Adhesive Thickness		Total Thickness		Adhesion Strength		Tensile Strength		Elongation %	Dielectric kV	°C	Insulation Class		Temperature Range		Comments
			mil / mm	mil / mm	mil / mm	oz/in g/cm	lbs/in kg/cm	%	°C	Min °F	Max °F	Min °C				Max °C				

### FILM-FEP

C	Clear	S	2.0	0.051	1.5	0.025	3.5	0.076	20	220	8	1.4	275	9.0	155	-100	400	-73	204	
2355-2	Clear	S	2.0	0.051	1.5	0.025	3.5	0.076	20	220	8	1.4	275	9.0	155	-100	400	-73	204	

### FILM-POLYESTER

M50	White	S	1.0	0.025	1.7	0.043	2.7	0.069	25	276	25	4.5	100	5.0	130	-100	350	-73	177	
M52	Clear	S	1.0	0.025	1.5	0.038	2.5	0.064	30	331	25	4.5	100	5.0	130	-100	350	-73	177	UL Guide OANZ2, File E51201, UL510
M54	Yellow	R	1.0	0.025	1.5	0.038	2.5	0.064	45	441	25	4.5	100	5.0	130	0	325	-18	163	MIL-I-15126-MFT2.5
M56	Clear	R	1.0	0.025	1.5	0.038	2.5	0.064	45	496	25	4.5	100	5.0	130	0	325	-18	163	MIL-I-15126-MFT2.5 UL Guide OANZ2 File E51201
M57	Yellow	R	2.0	0.051	1.5	0.038	3.5	0.089	50	551	50	8.9	120	7.0	130	0	325	-18	163	
M60	Clear	A	1.0	0.025	1.5	0.038	2.5	0.064	30	331	25	4.5	100	5.0	130	-20	325	-29	163	UL Guide OANZ2, File E51201, MIL-I-15126-MF2.5
M64	Yellow	R	1.0	0.025	1.5	0.038	2.5	0.064	50	551	25	4.5	100	5.0	130	0	325	-18	163	UL Guide OANZ2, File E51201, MIL-I-15126-MFT2.5
M66	Green	S	1.0	0.025	1.5	0.038	2.5	0.064	25	276	25	4.5	100	5.0	130	-100	350	-73	177	
M69	Clear	A/A	1.0	0.025	3.0	0.076	4.0	0.102	30	331	25	4.5	100	5.0	130	-20	325	-29	163	Available only with Liner
M97	Yellow	A	1.0	0.025	1.5	0.038	2.5	0.064	35	386	25	4.5	100	5.0	130	-20	325	-29	163	MIL-I-15126-MFT2.5 UL Guide OANZ2 File E51201
M98	Blue	S	2.0	0.051	1.8	0.046	3.8	0.097	18	198	50	8.9	120	7.0	130	-100	350	-73	177	
M99	Yellow	A	2.0	0.051	1.5	0.038	3.5	0.089	40	441	50	8.9	120	7.0	130	-20	325	-29	163	
M705	Black	A	1.0	0.025	1.5	0.038	2.5	0.064	30	331	25	4.5	100	5.0	130	-20	325	-29	163	UL Guide OANZ2, File E51201
M706	White	A	1.0	0.025	1.5	0.038	2.5	0.064	30	331	25	4.5	100	5.0	130	-20	325	-29	163	UL Guide OANZ2, File E51201, UL510
M716	Violet	R	1.0	0.025	1.1	0.028	2.1	0.053	18	198	25	4.5	100	5.0	130	0	325	-18	163	
M717	Red	S	1.0	0.025	2.8	0.071	3.8	0.097	30	276	25	4.5	100	5.0	130	-100	350	-73	177	
M730	Green	S	1.5	0.038	1.0	0.025	2.5	0.064	25	276	35	6.3	100	5.0	130	-100	350	-73	177	
M734	Orange	R	1.0	0.025	0.6	0.015	1.6	0.041	6	66	25	4.5	100	5.0	130	0	325	-18	163	
M741	Blue	S	1.0	0.025	2.0	0.051	3.0	0.076	25	276	25	4.5	100	5.0	130	-100	350	-73	177	
M746	Rd/Bl/Cl	S	1.0	0.025	0.8	0.020	1.8	0.046	13	143	25	4.5	100	—	130	-100	350	-73	177	
M751	Yellow	S	1.0	0.025	2.0	0.051	3.0	0.076	25	276	25	4.5	100	5.0	130	-100	350	-73	177	
M758	Black	S	1.0	0.025	1.5	0.038	2.5	0.064	25	276	25	4.5	100	5.0	130	-100	350	-73	177	
M765	White	R	1.0	0.025	1.5	0.038	2.5	0.064	25	276	25	4.5	100	5.0	130	-20	325	-29	163	UL Guide OANZ2, File E51201, UL510
M783	Pink	R	2.0	0.051	1.7	0.043	3.7	0.094	35	386	50	8.9	120	7.0	130	0	325	-18	163	
M787	Clear	R	5.0	0.127	1.5	0.038	6.5	0.165	60	661	100	17.9	100	10.0	130	0	325	-18	163	
M788	Aqua	R	1.0	0.025	0.5	0.013	1.5	0.038	5	55	25	4.5	100	5.0	130	0	325	-18	163	
M797	Mustard	R	1.0	0.025	2.0	0.05	3.0	0.076	30	331	25	4.5	100	5.0	130	0	325	-18	163	
M803	Blue	S	1.0	0.025	2.0	0.051	3.0	0.076	25	276	25	4.5	100	5.0	130	-100	350	-73	177	
M815	Clear	S	1.0	0.025	2.0	0.051	3.0	0.076	30	331	25	4.5	100	5.0	130	-100	350	-73	177	
M823	Blue	S	1.0	0.025	1.8	0.046	2.8	0.071	30	331	25	4.5	100	5.0	130	-100	350	-73	177	Silicone Coating Backing
M824	Blue	S	1.0	0.025	1.5	0.038	2.5	0.064	30	331	25	4.5	100	5.0	130	-100	350	-73	177	
M827	Red	S	1.0	0.025	2.0	0.051	3.0	0.076	30	331	25	4.5	100	5.0	130	-100	350	-73	177	
M832	Blue	S	2.0	0.051	1.5	0.038	3.5	0.089	35	386	50	8.9	120	7.0	130	-100	350	-73	177	
M835	Blue	S	5.0	0.127	1.5	0.038	6.5	0.165	30	331	100	17.9	100	10.0	130	-100	350	-73	177	
M851	Green	R	1.0	0.025	2.0	0.051	3.0	0.076	15	165	25	4.5	100	6.0	130	0	350	-18	177	
M852	Green	R	2.0	0.051	2.0	0.051	4.0	0.102	15	165	50	8.9	120	7.0	130	0	350	-18	177	
M855	Green	R	5.0	0.127	2.0	0.051	7.0	0.178	6	66	100	17.9	100	10.0	130	0	350	-18	177	
M887	Emerald	S	2.0	0.051	1.5	0.038	3.5	0.089	40	441	25	4.5	120	7.0	130	-60	350	-51	177	
M897	Olive	R	1.0	0.025	2.0	0.051	3.0	0.076	20	220	25	4.5	100	5.0	130	0	325	-18	163	

### FILM-POLYIMIDE

2345-1	Amber	S	1.0	0.025	1.5	0.038	2.5	0.064	25	276	30	5.4	50	6.5	180	-100	500	-73	260	UL Guide OANZ2, File E66639, UL510
2345-2	Amber	S	2.0	0.051	1.5	0.038	3.5	0.089	25	276	50	8.9	75	10.0	180	-100	500	-73	260	UL510 E6639
2345-5	Amber	S	5.0	0.127	1.5	0.038	6.5	0.165	20	221	150	26.8	75	17.0	180	-100	500	-73	260	
K104	Amber	S	0.5	0.013	1.0	0.025	1.5	0.038	15	165	10	1.8	25	4.0	180	-100	500	-73	260	
K250	Amber	S	1.0	0.025	1.7	0.043	2.7	0.069	30	220	30	5.4	50	7.0	180	-100	500	-73	260	UL Guide OANZ2, File E51201, UL510
K350	Amber	S	2.0	0.051	1.5	0.038	3.5	0.089	20	220	50	8.9	75	10.0	180	-100	500	-73	260	UL Guide OANZ2, File E51201, UL510
K102	Amber	A	1.0	0.025	1.5	0.038	2.5	0.064	30	331	30	5.4	50	7.0	155	-20	350	-29	177	Clean Release Silicone (CRS) adhesive
K103	Amber	A	1.0	0.025	1.5	0.038	2.5	0.064	25	276	30	5.4	50	7.0	155	-20	350	-29	177	UL Guide OANZ2, File E51201, UL510
K109	Amber	A	2.0	0.051	1.5	0.038	3.5	0.089	30	331	50	8.9	75	10.0	155	-20	350	-29	177	
K290ESD	Amber	S	1.0	0.025	1.7	0.043	2.7	0.069	20	220	30	5.4	50	7.0	180	-100	500	-73	260	
K100	Amber	S/S	1.0	0.025	3.5	0.089	4.5	0.114	20	220	30	5.4	50	7.5	180	-100	500	-73	260	Available only with Liner

### FILM-PTFE

Skived																				
2045-2	Gray	S	2.0	0.051	1.5	0.038	3.5	0.089	30	331	15	2.7	325	7.5	180	-40	500	-40	260	
2045-3	Gray	S	3.0	0.076	1.5	0.038	4.5	0.114	35	386	20	3.6	350	9.5	180	-40	500	-40	260	
2045-5	Gray	S	5.0	0.127	1.5	0.038	6.5	0.165	40	441	30	5.4	400	13.0	180	-40	500	-40	260	
2045-10	Gray	S	10.0	0.25	1.5	0.038	11.5	0.292	50	551	60	10.7	450	19.5	180	-40	500	-40	260	

Continued next page

Part Number	Color	Adhesive System	Backing Thickness		Adhesive Thickness		Total Thickness		Adhesion Strength		Tensile Strength		Elongation	Dielectric	Insulation Class		Temperature Range		Comments
			mil / mm	mil / mm	mil / mm	mil / mm	oz/in	g/cm	lbs/in	kg/cm	%	kV			°C	Min °F	Max °F	Min °C	

### FILM-PTFE *Continued from previous page*

Skived																				
2042-2	Gray	A	2.0	0.051	1.5	0.038	3.5	0.089	25	276	15	2.7	300	7.0	130	-100	250	-73	121	
2042-3	Gray	A	3.0	0.076	1.5	0.038	4.5	0.114	30	331	20	3.6	375	10.0	130	-100	250	-73	121	
2042-5	Gray	A	5.0	0.127	1.5	0.038	6.5	0.165	35	441	30	5.4	400	13.5	130	-100	250	-73	121	
2042-10	Gray	A	10.0	0.25	1.5	0.038	11.5	0.292	55	661	55	10.7	450	19.0	130	-100	250	-73	121	
TV350	White	S	2.0	0.051	1.5	0.038	3.5	0.089	25	276	15	2.7	250	7.8	180	-100	500	-73	260	MIL-I-123594C Type 1, Class 1, A-A-59474
T	White	S	3.0	0.076	1.5	0.038	4.5	0.114	30	331	20	3.6	275	10.0	180	-100	500	-73	260	MIL-I-123594C Type 1, Class 2, A-A-59474
TV	White	S	5.0	0.127	1.5	0.038	6.5	0.165	35	441	30	5.4	275	13.0	180	-100	500	-73	260	MIL-I-123594C Type 1, Class 4, A-A-59474
TH	White	S	10.0	0.25	1.5	0.038	11.5	0.292	55	661	60	10.1	300	18.0	180	-100	500	-73	260	

### High-Modulus

2253-2	Gray	A	2.0	0.051	1.5	0.038	3.5	0.089	30	331	30	5.0	150	9.5	130	-40	350	-40	177	
2254-2	Gray	S	2.0	0.051	1.5	0.038	3.5	0.089	35	441	30	5.4	150	9.0	150	-40	500	-40	260	
2255-2	Gray	S	2.0	0.051	1.5	0.038	3.5	0.089	30	331	30	5.0	150	9.0	180	-100	500	-73	260	MIL-I-123594C Type 1, Class 1, A-A-59474
2255-3	Gray	S	3.0	0.076	1.5	0.038	4.5	0.114	35	386	45	8.0	175	11.0	180	-100	500	-73	260	MIL-I-123594C Type 1, Class 2, A-A-59474
2255-5	Gray	S	5.0	0.125	1.5	0.038	6.5	0.165	40	441	60	10.7	275	15.0	180	-100	500	-73	260	MIL-I-123594C Type 1, Class 4, A-A-59474
2255-6	Gray	S	6.0	0.152	1.5	0.038	7.5	0.191	45	496	65	11	200	18.0	—	-100	500	—	—	

2255 product series also available with silicone adhesive in 4, 6, 7 and 10 mil. backing thickness, please consult factory.

HM350	White	S	2.0	0.051	1.5	0.038	3.5	0.089	25	276	25	4.5	150	8.0	180	-100	500	-73	260	MIL-I-123594C Type 1, Class 1, A-A-59474
HM426	Gray	S	2.05	0.064	10.0	0.025	3.5	0.089	25	276	25	4.5	150	8.0	180	-100	500	-73	260	
HM430	White	A	2.0	0.064	1.5	0.025	3.5	0.089	25	276	25	4.5	150	8.0	155	-20	350	-29	177	
HM650	White	S	5.0	0.127	1.5	0.038	6.5	0.165	30	331	45	8	200	13.5	180	-100	500	-73	260	MIL-I-123594C Type 1, Class 4, A-A-59474

### Extruded

2265-2	Gray	S	2.0	0.051	1.5	0.038	3.5	0.089	35	386	25	4.0	200	8.0	—	-100	500	-73	260	
2265-5	Gray	S	2.0	0.051	2.0	0.051	7.0	0.078	45	496	65	11.8	250	15.0	—	-100	500	-73	260	
2275-2	Rust	S	2.3	0.051	1.9	0.048	4.2	0.107	40	441	45	8.0	110	11.0	—	-100	500	-73	260	
2283-2	Rust	A	2.0	0.051	2.0	0.051	4.0	0.102	30	331	30	5.0	150	10.0	—	-40	350	-40	177	
2285-2	Rust	S	2.0	0.051	1.5	0.038	3.5	0.089	30	331	30	5.0	175	9.0	—	-100	500	-73	260	
2285-5	Rust	S	5.0	0.127	1.5	0.038	6.5	0.165	40	441	75	13.0	200	16.0	—	-100	500	-73	260	

### FILM-RULON

RU	Rose	S	8.0	0.203	2.0	0.051	10.0	0.254	25	276	20	3.6	225	—	155	-100	500	-73	260	
RU101	Rose	A	8.0	0.203	2.3	0.058	10.3	0.262	20	220	20	3.6	225	—	155	-20	350	-29	177	

### FILM-UHMW

2300-5R	Natural	R	5.0	0.127	2.0	0.051	7.0	0.178	55	772	40	7.0	350	—	—	-40	225	-40	107	
2300-10R	Natural	R	10.0	0.25	2.0	0.051	12.0	0.305	55	606	80	14.5	400	—	—	-40	225	-40	107	
2302-3R	Natural	A	3.0	0.076	1.5	0.038	4.5	0.114	35	386	20	3.6	300	—	—	-40	225	-40	107	
2302-5R	Natural	A	5.0	0.127	1.5	0.038	6.5	0.165	45	496	40	7.0	350	—	—	-40	225	-40	107	
2302-10R	Natural	A	10.0	0.25	1.5	0.038	11.5	0.292	50	551	80	14.5	425	—	—	-40	225	-40	107	
2302-20R	Natural	A	20.0	0.5	1.5	0.038	21.5	0.546	50	551	145	26.3	500	—	—	-40	225	-40	107	

For 23XX product series, a blue PE liner is standard. Call for availability of black film.

### GLASS-CLOTH

2905-7R	White	S/S	4.5	0.114	2.5	0.064	7.0	0.178	40	441	175	31.3	<10	—	180	-100	500	-73	260	Available only with liner
2905-10R	White	S/S	6.5	0.165	4.0	0.102	10.5	0.267	25	276	225	40.2	<10	8.0	180	-100	500	-73	260	Available only with liner
2915-7	White	S	4.5	0.114	2.5	0.064	7.0	0.178	40	441	160	26.8	—	4.5	180	-100	500	-73	260	MIL-I-19166C
2915-10	White	S	5.5	0.140	4.5	0.114	10.0	0.254	40	441	175	31.3	—	5.0	180	-100	500	-73	260	
2916-7	White	S	4.5	0.114	3.0	0.076	7.0	0.178	45	441	165	29.0	—	4.3	—	-100	500	-73	260	
G551	White	R	4.5	0.114	2.5	0.064	7.0	0.178	50	551	150	26.8	<5	4.0	130	0	350	-18	177	UL Guide OAN22, File E51201
G561	White	S	4.5	0.114	2.8	0.071	7.3	0.185	35	386	150	26.8	<5	3.5	180	-100	500	-73	260	MIL-I-19166C-7MIL-QPL
G565	White	S	4.5	0.114	2.8	0.071	7.3	0.185	35	386	150	26.8	<5	3.5	200	-100	500	-73	260	UL Guide OAN22, File E51201, UL510
G569	White	A	4.5	0.114	2.5	0.064	7.0	0.178	30	331	150	26.8	<5	3.0	155	-20	350	-29	177	UL Guide OAN22, File E51201

### GLASS-FOIL

06004	Alum.	S	2.5	0.064	3.5	0.089	8.0	0.203	60	661	155	28.1	—	—	—	-100	500	-73	260	
06005	Alum.	S	2.5	0.064	3.5	0.089	8.0	0.203	70	772	150	27.0	7	—	—	-100	500	-73	260	
2925-7	Alum.	S	2.5	0.064	4.5	0.114	7.0	0.178	60	661	130	23.6	7	—	—	-100	500	-73	260	
2925-11	Alum.	S	7.5	0.191	3.5	0.089	11.0	0.279	75	827	200	35.7	7	—	—	-100	500	-73	260	
2995-11R	Alum.	S	7.0	0.178	5.0	0.076	12.0	0.305	45	496	150	27.0	5	—	—	-100	500	-73	260	

### GLASS-SILICONE

23816	White	S	8.0	0.203	4.0	0.102	12.0	0.305	50	551	100	18.0	—	7.0	—	-100	500	-73	260	
2965-8R	Blue	S	7.0	0.178	3.5	0.089	10.5	0.267	45	496	100	18.0	15	4.0	—	-100	500	-73	260	
2975-8R	White	S	7.0	0.178	3.5	0.089	10.5	0.267	50	551	150	27.0	5	7.0	—	-100	500	-73	260	
H7575	White	S	17.5	0.44	3.5	0.089	21.0	0.553	50	551	180	32.7	—	—	—	-100	500	-73	260	
H7525	White	S	15.0	0.38	2.5	0.064	17.5	0.445	50	551	125	22.0	—	—	—	-100	500	-73	260	

For 2386, 2965-8R, 2975 and H7575, a yellow-dimpled PVC liner is standard. For H7525, a Kraft paper is standard.

Saint-Gobain Performance Plastics is a world leader in the production of differentiated products based in polymer and fluoropolymer technology with our family of acquisitions that includes Furon, Norton, Chemfab and Norwood. Saint-Gobain offers a wide range of non-adhesive products including PTFE and silicone-coated fabrics, belting, fluoropolymer films, release liners and foams.

These engineered products are used primarily by OEM servicing industries such as fuel processing, transportation, electronics, health-care, construction, packaging and industrial equipment. Our combined expertise in fabrics, films, foams and coatings gives you confidence in our team approach to providing solutions to critical applications.

Contact your nearest Saint-Gobain Performance Plastics representative for more details.

DISTRIBUTED BY:

**Limited Warranty:** For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

**NOTE:** Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.



Saint-Gobain Performance Plastics Corporation  
14 McCaffrey Street  
Hoosick Falls, NY 12090-0320  
Tel: (518) 686-7301  
Fax: (518) 686-4840  
www.plastics.saint-gobain.com