



KYDEX[®] 200
General purpose grade

Introduction

KYDEX[®] 200 is a proprietary thermoplastic sheet that is cost competitive with other thermoplastics while providing excellent extensibility, good impact resistance and excellent solvent resistance.

General Information

Based on independent laboratory testing it meets the requirements of Underwriter's Laboratories, Inc.[®] Std 94 V-0 in all thicknesses. It has 534 J/m (10 ft-lbs/in) of Notched Izod impact resistance.

Suggested Applications

- * Aircraft Interiors
- * Equipment Housings
- * Medical Products
- * Miscellaneous Applications

Features

- * available in seven thicknesses from 0.71mm (0.028") and up, in eight distinctive textures and limited colors
- * delivers performance advantages at an effective cost
- * among the most rigid of thermoforming materials, with a high modulus elasticity
- * particularly effective for pressure forming and/or where a part will be painted
- * meets requirements of 94 V-0 in all thicknesses as tested by an independent lab
- * excellent forming results, uniform wall thicknesses and crisp detail
- * easy machining and fabricating using conventional methods and equipment
- * endorsed by the Royal Institute of Public Health for conformance to the standard of Hygenic Merit

Environmental and Safety Considerations

Kleerdex is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health and environmental protection. We support the safe handling of our products. Please contact our Technical Service department at 800.682.8758 for resources or visit our website: www.kydex.com. For Material Safety Data Sheets, please call 800.325.3133.

Kleerdex Company, LLC

ISO 9001 and ISO 14001 Certified


Customer Service

6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Outside the US: +1.570.389.5814
Fax: 800.452.0155, +1.570.387.7786
Email: info@kleerdex.com

Technical Service

Phone: 800.682.8758 ext. 581
Fax: +1.570.387.8722
Outside the US: +1.570.387.6997 ext.581

www.kydex.com



Durability by Design[®]



KYDEX® 200

General purpose grade

Physical Properties

Property	Test Method	Typical Value ¹	
Specific Gravity	ASTM D-792	1.35	
Tensile Strength	ASTM D-638	42 MPa	6,100 psi
Flexural Strength	ASTM D-790	63 MPa	9,100 psi
Modulus of Elasticity	ASTM D-790	2,206 MPa	320,000 psi
Notched Izod Impact Resistance, @ 23°C (73°F)	ASTM D-256	534 J/m	10 ft-lbs/in
Rockwell Hardness (R Scale)	ASTM D-785	94	
Heat Deflection Temperature (HDT) @ 264 psi (1.8 MPa) annealed	ASTM D-648	78°C	173°F
Flammability: Independent Test Lab	UL Standard 94	V-0	
Forming Temperature		163 - 200°C	325 - 390°F
DIN 4102-B1		Pass at 0.71 mm (0.028")	
¹ Values based upon 3.18mm (0.125") sheet unless otherwise specified. Not intended for specification purposes.			

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our products. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.

Kleerdex Company, LLC

ISO 9001 and ISO 14001 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA
 Phone: 800.325.3133, +1.570.389.5810
 Outside the US: +1.570.389.5814
 Fax: 800.452.0155, +1.570.387.7786
 Email: info@kleerdex.com

Technical Service

Phone: 800.682.8758 ext. 581
 Fax: +1.570.387.8722
 Outside the US: +1.570.387.6997 ext.581