

PRODUCT DATASHEET

LEXAN™ SGC100 Sheet

DESCRIPTION

LEXAN SGC100 Solar Grade Coextruded sheet for signs combines the impact strength of LEXAN polycarbonate sheet with a proprietary UV-resistant cap layer that provides long-term protection against weathering. LEXAN SGC100 sheet is backed by ten-year limited written warranty against yellowing, loss of light transmission and breakage. Providing long-lasting clarity over a wide range of environments, LEXAN SGC100 sheet offers extended service life and reduced life-cycle material costs. It is an excellent candidate for all types of thermoformed or flat signs, whether screen printed, painted, or decorated with vinyl graphics.

TYPICAL PROPERTY VALUES ♦

Property	Test Method	Units	Value
Physical			
Specific gravity	ASTM D792	-	1.20
Light Transmission @ .118" thickness	ASTM D1003	%	87
Rockwell Hardness	ASTM D785	-	M70,R118
Mechanical			
Tensile Strength	ASTM D638	psi	
Ultimate			9,500
Tensile Modulus	ASTM D638	psi	285,000
Flexural Strength	ASTM D790	psi	13,500
Flexural Modulus	ASTM D790	psi	340,000
Compressive Strength	ASTM D695	psi	12,500
Izod Impact Strength, up to 125 mils	ASTM D256A	ft-lbs/in	
Notched			12-16
Drop Ball Impact Strength, 1" dia.dart @ .236 thickness			
	SABIC Test ##	ft-lbs	
@ 73°F			>200
@ 0°F			>200
Thermal			
Coefficient of Thermal Expansion	ASTM D696	in/in/°F	3.75×10^{-5}
Heat Deflection Temperature	ASTM D648	°F	
@ 264 psi			260
@ 66 psi			280

- ♦ These typical values are not intended for specification purposes. If minimum certifiable properties are required please contact your local SABIC Innovative Plastics, Specialty Film & Sheet representative.
- # See actual Product Warranty for conditions that may apply.
- ## Measured by dropping a 25-pound dart (1" dia. tip) from a height of 8 feet.
- ™ LEXAN is a trademark of SABIC.


UL File Number: E121562

PRODUCT DATASHEET

LEXAN™ SGC100 Sheet


UV Resistance

LEXAN SGC100 sheet was exposed to accelerated QUV weathering. After exposure comparable to 10 years in South Florida, LEXAN SGC100 sheet showed only minimal in yellowness, light transmission, and clarity.



Impact Resistance

LEXAN SGC100 sheet has 30 up to times the impact strength of acrylic and 10 times that of "impact-modified" acrylic.



Americas Headquarters

SABIC Innovative Plastics
One Plastics Avenue
Pittsfield, MA 01201
USA
T +1-413-448-7125
Toll-free: 1-800-323-3783
F +1 (888) 443-2033
sfsustomerservice@sabic-ip.com

European Headquarters

SABIC Innovative Plastics
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 164 293684
F +31 164 293272
Sfs.info@sabic-ip.com

Pacific Headquarters

SABIC Innovative Plastics
Specialty Film & Sheet
1266 Nanjing Road (W)
16th Floor, Plaza 66
200040 Shanghai
China
T +86 21 62881088 ext. 6733
F +86 21 6288 0818

E-mail

sfsustomerservice@sabic-ip.com



* Trademark of SABIC Innovative Plastics IP BV

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right. SABIC Innovative Plastics is a trademark of SABIC Holding Europe BV

™ Trademark of SABIC.