

Saint-Gobain Performance Plastics-- Korton® ECTFE Fluoropolymer Film



Product Features:

- Outstanding release properties
- Performance from -254°C (-425°F) to 165°C (330°F)
- High dielectric strength
- Excellent chemical, radiation, weather and abrasion resistance
- Non-flammable
- Thermoformable
- Minimum thickness of 0.0005" (0.0127mm)
- Widths up to 64" (1625mm)
- Blue, clear and white colors

Technical Data:

	Test Method	Value
Specific Gravity	D-792	1.68
Water Absorption		<0.01%
Tensile Strength	D-882	8000psi
Elongation at Break	D-882	250%
Melt Point	D-3418	465°F
Continuous Use Temperature		300-340°F
Flammability	UL-94	V-0
Limiting Oxygen Index		

Total Plastics, Inc. will not be responsible for the use of this information relative to actual application. Users must make their own determination of its suitability for their specific application. No warranty is made for the fitness of any product, and nothing herein waives any of the seller's conditions of sale.