

Westlake® PMP Film
Made from TPX® Polmethylpentene Resin

Product Features:

- Lowest specific gravity of any known thermoplastic
- Exceptional electrical properties
- Good chemical resistance
- High heat resistance
- Excellent acoustical properties
- Transparency
- FDA compliant

Technical Data:

	Test Method	Value
Specific Gravity	D-792	.835
Water Absorption	D-570	0.01 @24 hours
Tensile Strength	D-882	4,110psi
Elongation at Break	D-882	10%
Melt Point	DSC	455°F
Continuous Use Temperature		212°F
Flammability	UL-94	HB
Limiting Oxygen Index	D-2863	38%

Total Plastics, Inc. will not be responsible for the use of this information relative to actual application. Users must make their own determination of its suitability for their specific application. No warranty is made for the fitness of any product, and nothing herein waives any of the seller's conditions of sale.